

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in
5 the application:

Listing of Claims:

1 Claim 1 (previously presented): A flexible, hollow waveguide for transmitting
2 radiation in visible and IR regions, comprising:

3 (a) a hollow, flexible tube having a transparent annular body defining a bore
4 with a smooth inner bore surface;

5 (b) a reflective metal layer disposed upon the smooth inner bore surface; and

6 (c) a composite of dielectric, sulfide-containing materials having a high
7 refractive index ratio, said sulfide-containing materials disposed upon said reflective
8 metal layer and forming a photonic, bandgap tube transmitting in the visible and IR
9 regions.

1 Claim 2 (original): The waveguide in accordance with claim 1, wherein said hollow,
2 flexible tube is composed of glass.

1 Claim 3 (original): The waveguide in accordance with claim 1, wherein said hollow,
2 flexible glass tube is composed of silica-glass.

1 Claim 4 (original): The waveguide in accordance with claim 1, wherein said
2 composite of dielectric, sulfide-containing materials comprise disparate refractive
3 indices of approximately 2:1.

1 Claim 5 (original): The waveguide in accordance with claim 4, wherein said metallic
2 layer is selected from a group of metals consisting of: Ag, Au, Cu, Pt, Ni, Mb, Al, and
3 combinations thereof.

1 Claim 6 (original): The waveguide in accordance with claim 1, further comprising:
2 (d) an outer layer surrounding the hollow, flexible tube.

1 Claim 7 (previously presented): The waveguide in accordance with claim 4, wherein
2 the composite of sulfide-containing materials respectively comprise paired composite
3 layers of cadmium sulfide and lead sulfide.

1 Claim 8 (previously presented): The waveguide of claim 4, wherein said outer layer
2 is composed of a material selected from a group of materials consisting of plastic,
3 and silicone.

1 Claim 9 (previously presented): A flexible, hollow waveguide, comprising:
2 (a) a flexible, hollow tube having a transparent annular body defining a bore
3 with a smooth inner bore surface;
4 (b) a metallic layer disposed upon the smooth inner bore surface; and

5 (c) a composite of dielectric materials disposed upon the metallic layer
6 featuring disparate refractive indices with a ratio of approximately 2.1, wherein the
7 composite of dielectric materials form sulfide-containing layers.

1 Claim 10 (previously presented): The waveguide in accordance with claim 9, wherein
2 said composite of dielectric materials respectively comprise two sulfide-containing
3 layers.

1 Claim 11 (original): The waveguide in accordance with claim 9, wherein said metallic
2 layer is selected from a group of metals consisting of: Ag, Au, Cu, Pt, Ni, Mb, Al, and
3 combinations thereof.

1 Claim 12 (previously presented): The waveguide in accordance with claim 9, further
2 comprising:
3 (d) an outer layer surrounding the hollow flexible tube.

1 Claim 13 (canceled).

1 Claim 14 (previously presented): The waveguide in accordance with claim 9, wherein
2 the composite of dielectric materials respectively comprise cadmium sulfide and lead
3 sulfide.

1 Claim 15 (previously presented): The waveguide in accordance with claim 11,
2 wherein said outer layer is selected from a group of materials consisting of plastic,
3 and silicone.

1 Claim 16 (previously presented): A flexible, hollow waveguide for transmitting
2 radiation in visible and IR regions, comprising:

3 (a) a hollow, flexible tube having a transparent annular body defining a bore
4 with a smooth inner bore surface; and

5 (b) a composite of dielectric, paired sulfide-containing materials having a high
6 refractive index ratio, said sulfide-containing materials disposed upon said hollow
7 tube, and forming a photonic, bandgap tube transmitting in the visible and IR
8 regions.

1 Claim 17 (previously presented): The waveguide in accordance with claim 16,
2 wherein said hollow, flexible tube is composed of glass.

1 Claim 18 (previously presented): The waveguide in accordance with claim 16,
2 wherein said hollow, flexible glass tube is composed of silica-glass.

1 Claim 19 (previously presented): The waveguide in accordance with claim 16,
2 wherein said composite of dielectric, sulfide-containing materials comprise disparate
3 refractive indices of approximately 2:1.

1 Claim 20 (previously presented): The waveguide in accordance with claim 19, further
2 comprising:

3 (d) an outer layer surrounding the hollow, flexible tube.

1 Claim 21 (previously presented): The waveguide in accordance with claim 16,
2 wherein the composite of sulfide-containing materials respectively comprise paired
3 composite layers of cadmium sulfide and lead sulfide.

1 Claim 22 (previously presented): The waveguide of claim 20, wherein said outer
2 layer is composed of a material selected from a group of materials consisting of
3 plastic, and silicone.

1 Claim 23 (previously presented): A flexible, hollow waveguide, comprising:

2 (a) a flexible, hollow tube having a transparent annular body defining a bore
3 with a smooth inner bore surface; and

4 (b) a composite of dielectric materials disposed upon the smooth inner bore
5 surface of said transparent annular body, featuring disparate refractive indices with a
6 ratio of approximately 2.1, wherein said composite of dielectric materials respectively
7 comprise two sulfide layers.

1 Claim 24 (canceled).

1 Claim 25 (previously presented): The waveguide in accordance with claim 23, further
2 comprising:

3 (d) an outer layer surrounding the hollow flexible tube.

1 Claim 26 (previously presented): The waveguide in accordance with claim 23,
2 wherein the composite of dielectric materials respectively comprise cadmium sulfide
3 and lead sulfide.

1 Claim 27 (previously presented): The waveguide in accordance with claim 25,
2 wherein said outer layer is selected from a group of materials consisting of plastic,
3 and silicone.

1 Claim 28 (previously presented): A method of fabricating a flexible, hollow
2 waveguide using liquid phase deposition, comprising the steps of:

3 (a) depositing a metallic layer on a smooth, inner bore surface of a hollow,
4 flexible, silica-glass tube; and

5 (b) depositing two sulfide-containing layers, cadmium sulfide and lead sulfide,
6 respectively, upon said metallic layer of step (a).

1 Claim 29 (canceled).

1 Claim 30 (canceled).

1 Claim 31 (previously presented): A method of fabricating a flexible, hollow
2 waveguide using liquid phase deposition, comprising the steps of:

3 (a) depositing at first layer of cadmium sulfide upon an inner, smooth bore
4 surface of a hollow silica-glass tube; and

5 (b) depositing at least a second layer of lead sulfide over said first layer of
6 cadmium sulfide.

1 Claim 32 (previously presented): The method in accordance with claim 31, wherein
2 multiple sulfide-containing layers of cadmium sulfide and lead sulfide, respectively,
3 are stack deposited upon said inner, smooth bore of said hollow tube.

1 Claim 33 (canceled).